

CARBODUR 600 AC

Standards	DIN 8555	E 6- UM - 60 GP
	DIN EN 14700	E Fe6

Characteristics CARBODUR 600 AC is an AC-weldable universal hard surfacing electrode with 120 % recovery for rebuilding of machine parts subject to combined wear from abrasion and impact. Suitable for deposits on mild steel, steel castings and manganese steel.
The pure weld deposit is only machinable by grinding.
The electrode has a soft but intensive welding character, a fine-structured seam surface and excellent slag-removal properties.
On high-carbon and crack-sensitive base materials, should be preheated to 200° – 300° C, depending on their composition and thickness. On highly crack-sensitive base materials and manganese steel, a buffer layer of CARBO 4370 MPR or CARBODUR MnCr is recommended.

Typical applications Rollers, dredger chains, conveyors, hammers, dredger equipment, mining and earth-moving equipment

Operating temperature

Welding instructions Guide electrode almost vertically with a short arc.

Hardness and recommendations for heat treatment	HRC as welded	Annealing: 5 h	Hardening oil - air
	ca. 59	780°C – 820° C	1000°C – 1050° C

Weld metal analysis (typical. wt %)	C	Si	Mn	Cr
	0,6	1,7	0,4	9

Current = + / ~ 50 V

Welding positions PA. PB. PC. PD. PE

Rebaking 1 h. 350 °C + (if required)

Flux-cored wire equivalent CARBO F- 600

Dia./Length	Amperage (A)	Pcs./ packet	Pcs./ carton	kg / 1000	kg / packet	kg / carton
2,5 x 350	60 – 90	221	884	22.6	5,0	20,0
3,2 x 350	90 – 120	135	540	37.0	5,0	20,0
4,0 x 450	110 – 160	86	344	76.0	6,0	24,0
5,0 x 450	150 – 200	56	225	106,8	6,0	24,0
6,0 x 450	180 – 250	37	148	162,6	6,0	24,0

Rev. 001/11