

Standards	DIN 8555	MF 20-MF-50-CTZ
	AWS A5.13	E CoCr-B

Characteristics The deposit of CARBO F-S 12 is a cobalt base alloy of austenitic-
ledeburitic structure with embedded CrW carbides.
The weld metal is highly resistant to corrosion, impact, abrasive
wear as well as thermal shocks and heavy mechanical impact.
.The deposit is only machinable by hard faced tools.

Welding instructions Working temperature should be kept between 400° and 600°C,
depending on base material and type of construction. Slow cooling,
if necessary oven cooling, is recommended for low alloyed and
austenitic steels.
Subsequent heat treatment (stress relief at 700°C approx.) is not
necessary, except on large structures.

Working temperature From room temperature up to + 600° C

Typical applications Hardfacing of cutting edges of long knives and other tools used in
the wood, plastic, paper, carpet and chemical industry.

Mechanical properties of all-weld metal (typical values)	At Rt. HRc	+ 300°C HRc	+ 600°C HRc	Melting- range °C	Density g/cm³
	ca. 48	ca. 37	ca. 32	1280-1320°C	8,7

Weld metal analysis (typical, wt. %)	C	Si	Mn	Cr	Mo	Ni	Co	Fe
	0,3	0,9	1	28	5,5	3	Base	3

Gas types EN 439 M13: 99% Argon with 1% Oxygen

Current = +

Current intensity	DIA (mm)	DIA (inch)	Volt	Amps	Delivering form
	1,2	3/64	19 - 22	120 - 220	G
	1,6	1/16	20 - 26	160 - 260	G
	2,0	5/64	22 - 27	220 - 280	G
	2,4	3/32	24 - 28	260 - 340	G
	2,8	7/64	25 - 29	300 - 400	S

Delivering form **O = Flux cored wire self shielding**
G = Flux cored wire for shielded arc welding
S = Flux cored wire for submerged arc welding

Coils, weight B/BS 300 = 15 kg B 450 = 30 kg pay off pack = 150 / 300 kg

Rev. 000

Statements on composition and application are just for the applier's information. Statements on mechanical properties always refer to the all-weld-metal according to valid standards. Carbo-Weld may change the characteristics of its products without notice. We recommend the applier to check our products for their special application autonomously.